

CLAIMS

1. A method of producing a fluoropolymer aqueous dispersion which comprises carrying out a concentration
5 treatment comprising a concentration operation of a pretreatment fluoropolymer aqueous dispersion, wherein said pretreatment fluoropolymer aqueous dispersion is obtained by carrying out a polymerization in an aqueous medium in the presence of a fluorine-containing surfactant
10 (A),
said fluorine-containing surfactant (A) is a fluorine-containing surfactant having an octanol/water partition coefficient of 1.5 to 3.5.
- 15 2. The method of producing a fluoropolymer aqueous dispersion according to Claim 1, wherein the ratio $[M^1/M^0]$ between the mass $[M^0]$ of the fluorine-containing surfactant (A) in the pretreatment fluoropolymer aqueous dispersion and the mass $[M^1]$ of the
20 fluorine-containing surfactant (A) removed by carrying out the concentration operation once is not lower than 0.5.
3. The method of producing a fluoropolymer aqueous dispersion according to Claim 1,
25 wherein the ratio $[M^1/M^0]$ between the mass $[M^0]$ of the fluorine-containing surfactant (A) in the pretreatment fluoropolymer aqueous dispersion and the mass $[M^1]$ of the fluorine-containing surfactant (A) removed by carrying out the concentration operation once is not lower than 0.6.
30
4. The method of producing fluoropolymer aqueous dispersion according to Claim 1,
wherein the ratio $[M^1/M^0]$ between the mass $[M^0]$ of the
35 fluorine-containing surfactant (A) in the pretreatment fluoropolymer aqueous dispersion and the mass $[M^1]$ of the

fluorine-containing surfactant (A) removed by carrying out the concentration operation once is not lower than 0.7.

5 5. The method of producing a fluoropolymer aqueous dispersion according to Claim 1, 2, 3 or 4, wherein the fluoropolymer aqueous dispersion has a solid matter concentration of 30 to 80% by mass.

10 6. The method of producing a fluoropolymer aqueous dispersion according to Claim 1, 2, 3, 4 or 5, wherein the fluorine-containing surfactant (A) has an octanol/water partition coefficient of 1.5 to 3.0.

15 7. The method of producing a fluoropolymer aqueous dispersion according to Claim 1, 2, 3, 4, 5 or 6, wherein a fluoropolymer constituting the pretreatment fluoropolymer aqueous dispersion comprises a tetrafluoroethylene homopolymer and/or a modified polytetrafluoroethylene.

20 8. The method of producing a fluoropolymer aqueous dispersion according to Claim 1, 2, 3, 4, 5 or 6, wherein a fluoropolymer constituting the pretreatment fluoropolymer aqueous dispersion is a perfluoropolymer.

25 9. A fluoropolymer aqueous dispersion which is obtained by the method of producing a fluoropolymer aqueous dispersion according to Claim 1, 2, 3, 4, 5, 6, 7 or 8.

30 10. A fluoropolymer aqueous dispersion containing a particle comprising a fluoropolymer dispersed in an aqueous medium, wherein said fluoropolymer aqueous dispersion contains a fluorine-containing surfactant (A) in an amount of not
35 smaller than 0.1 ppm but not greater than 5% by mass and

has a solid matter concentration of 30 to 80% by mass, said fluorine-containing surfactant (A) has an octanol/water partition coefficient of 1.5 to 3.5.

- 5 11. The fluoropolymer aqueous dispersion according to Claim 10,
wherein the fluorine-containing surfactant (A) is the one caused to be present in carrying out a polymerization in the aqueous medium for obtaining the fluoropolymer.
- 10 12. A fluoropolymer powder which is obtained by drying a wet powder obtained by coagulation of the fluoropolymer aqueous dispersion according to Claim 9, 10 or 11.
- 15 13. A fluoropolymer molding which is obtained by carrying out a molding/processing using the fluoropolymer aqueous dispersion according to Claim 9, 10 or 11 or the fluoropolymer powder according to Claim 12.